

Harbison-Walker
Mixing and Using Instructions
HARWACO BOND (DRY)

This product is an air setting mortar for laying fire brick.

When using part of a bag, first dry mix entire bag. Use clean mixing equipment. Do not lose any of the liquid during mixing.

FOR TROWELED JOINTS: The water required is up to 3 1/4 gallons (U.S.) (12.3 liters) of water per 100 lbs (45.4 kgs) of dry mortar. Only clean water suitable for drinking should be used.

DIPPED JOINTS FOR: Mix in same manner as for troweled joints adding water in small amounts until desired consistency is obtained. Too much water will reduce mortar strength.

Thin brick joints give best results. Each joint should be completely filled with mortar.

Review Material Safety Data Sheet and Warning Labels